

polytec High Pressure Laminate

General Information

polytec's range of Laminate and Benchtops are designed for applications such as kitchen worktops, countertops, bathroom vanities and laundry benchtops where a durable decorative surface is required.

Features

- Tough and durable
- Resistant to cracking, chipping, chemicals and reagents
- Industry relevant colour range
- Standard Laminates(Non-Postformable) and Postformable Laminates to Tight Form in most colours on 33, 40 and 50mm substrate

Environmental/Safety

polytec is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products.

PHYSICAL PROPERTIES	UNIT	TYPICAL PROPERTY	TEST METHOD
Density	Kg/m3	1350 - 1450	ASTM D 792-1
Dimensional Tolerance			
Length	mm	± 5	BS EN 438-2
Width	mm	± 5	
Thickness	mm	± 0.1	
Colour Stability		Blue wool standard Min 6	BS EN 438-2
Thickness Swell (24hr @ 20°C)	%	≤3.5	BS EN 317
Resistance to Impact	N	>20	BS EN 438-2
Resistance to Scratch	N	≥ 3	BS EN 438-2
Resistance to Wear	Revolutions	≥ 350	BS EN 438-2
Resistance to Steam		≥ 4	BS EN 438-2
Dry Heat Resistance, 180°C			
Finishes		≥ 4	BS EN 438-2
Resistance to Staining			
Group 1 + 2		≥ 5	BS EN 438-2
Group 3 + 4		≥ 4	
Resistance to Boiling Water		No Visible Change	BS EN 438-2
Dimensional Stability at elevated temperature	%	L ≤ 0.7 , T ≤ 1.2	BS EN 438-2

Fire Hazard Indices		
Ignitability Index	10 - 14	
Spread of Flame Index	0 - 8	AS/NZS 1530.3
Heat Evolved Index	2 - 6	
Smoke Development Index	2 - 4	

Chemical Resistance Test Results

polytec always recommend prompt clean-up of all spills on its decorative surfaces and the surface maintained in accordance with our Care and Maintenance instructions.

Performance	Chemical
No visible effect	Water, alcohol 96%, isopropanol, Petrol, amy1 acetate, acetone, household soap, detergents for dishwashing by hand, ammonium hydrate 10%, ketchup, cooking oil, trisodium phosphate 1%, coffee, tea, milk, acetic acid, caustic soda (<10%), citric acid 10%, wine, lipstick, grapefruit juice, wax, shoe polish, ink ballpoint pen, spirit dye pen, marking ink, hand cream
Slight Effect/No Effect if completely removed within 10-15 minutes	Hydrogen Peroxide 30%, hypochlorite bleach, hair dye, mercury chromate 2%, iodine, hydrochloric acid (<10%), phosphoric acid (10%), caustic soda (>10%)
Surface attack/necessitating immediate removal	Hydrochloric Acid (>10%, nitric acid (>10%), Sulphuric Acid (>10%)

Contact

For further information on this product, please contact the following:

Polytec Laminates, No. 1, Jalan Teknologi Utama PLO2, Kawasan Perindustrian Mengkibol, 86000 Kluang, Johor, Malaysia Telephone: +60 (7) 776 2600 Fax: +60 (7) 776 2608

Whilst the information contained in this document is based on data, which, to the best of our knowledge, was accurate and reliable at the time of preparation, we can accept no responsibility for errors and omissions. The provision of this information should not be construed as a recommendation to use any of our products in violation of any patent rights or breach of any statute or regulation. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, we can accept no responsibility for any loss or damage caused by any person acting or refraining from action as a result of this information.
